











TECHNICAL DATA
Oxide Polishing

Application area	Product name	Abrasive type	Gran size	pH	Additions of chemicals or water	Container size
Silicium-oxide						
 Very ductile materials and other non-ferrous metals. Ceramics	OP-S	Colloidal silica	0.25 µm (agglomerated)	Alkali (pH: 9.8)	Yes (additive)	1 l 5 l
 Very ductile materials and other non-ferrous metals. Ceramics. NonDry version to prevent tube clogging	OP-S NonDry	Colloidal silica	0.25 µm (agglomerated)	Alkali (pH: 9.8)	Yes (additive)	1 l 5 l
 Heterogeneous materials like composites. Carbon- and low alloy steels	OP-U	Colloidal silica	0.04 µm	Alkali (pH: 9.8)	No	1 l 5 l
 Heterogeneous materials like composites. Carbon- and low alloy steels. NonDry version to prevent tube clogging	OP-U NonDry	Colloidal silica	0.04 µm	Alkali (pH: 9.8)	No	1 l 5 l
 High alloy steels ad nickel based alloys	OP-A	Alumina	0.1 µm	Acidic (pH: 3-3.5)	Yes (water)	500 ml

Find Safety Data Sheets (SDSs) on [struers.com](https://www.struers.com)



TECHNICAL DATA
Oxide / Alumina Polishing

Application area	Product name	Abrasive type	Gran size μm	Before use	Container size
Aluminum-oxide					
	AP-A	Agglomerated alpha alumina	5 μm , 1 μm , 0.3 μm	To be mixed with demineralized water	1 kg
	AP-D	Degglomerated gamma alumina	0.05 μm	To be mixed with demineralized water	1 kg
	AP-D	Degglomerated alpha alumina	1 μm , 0.3 μm , 0.1 μm	To be mixed with demineralized water	1 kg

Find Safety Data Sheets (SDSs) on [struers.com](https://www.struers.com)